

20-20

Fibre Cement Board

Technical Data Sheet

Technical Specification

Test Subject	Test	Results	
		9mm Board	12mm Board
Density Dry (ex works)	BS EN 12467	1400 Kg/m3 +/- 5%	
pH Levels		10-11	
Bending Strength (mor) - wet (average)	BS EN 12467	13.2 MPa (class 2)	14 MPa (class 3)
Reaction to Fire	BS EN 13501-1	A1 Non-combustible	
Fire Resistance for non-load bearing walls (steel frame)	BS EN 1364-1	60 & 90 minutes (9mm thickness)	
Thermal Conductivity	BS EN 12664	0.160W/m.K	
Thermal Resistance	BS EN 12664	0.055m2.K/W	
Weather Resistance	BS EN 12467	Category A Pass	
Water Impermeability	BS EN 12467	Category A Pass	
Soak / Dry	BS EN 12467	56 Days Pass	
Heat / Rain	BS EN 12467	50 Cycles Pass	
Freeze / Thaw	BS EN 12467	100 Cycles Pass	
Moisture Movement (After immersion in water)	BS EN 12467	0.1%	
Screw Withdrawal Resistance (Pull Out)	BS EN 320	0.85kN	1.16kN



RESISTANT
BUILDING PRODUCTS (2025) LTD

Appearance and Dimension

The 20-20 Fibre Cement Boards are supplied as a rectangular board with square edges. The surface texture is smooth on the front and lightly textured at the back. Each pallet contains 52 sheets at 36kg for 9mm boards and 40 sheets at 48kg for 12mm boards.

Thickness : 9mm & 12mm

Board Size : 2400mm x 1200mm

www.resistant.co.uk | E: info@resistant.co.uk | T: +44 (0)28 9621 5555

©2020. Resistant Building Products Ltd. All rights reserved.